



# CABINET COAT

## TRIM & CABINET ENAMEL

### SATIN FINISH CC65

#### Features

- Urethane acrylic cabinet and trim finish
- Resists chipping, scuffing, food stains, grease & water
- Super adhesion
- Waterborne formula provides an ultra smooth "factory-like" finish
- Durable satin finish

#### Recommended For

Cabinets, Metal, New & Previously Painted Wood, Furniture, Woodwork, Doors Trim.

#### General Description

Cabinet Coat is the ultimate finish for refurbishing kitchen and bathroom cabinets, shelving, furniture, trim & crown moulding and other interior applications that require an ultra smooth, factory like finish with long lasting beauty. Its superior adhesion allows painting difficult surfaces, even polyurethane and varnish, without using a primer. Cabinet Coat offers excellent flow and levelling, superior stain resistance and an extremely durable satin finish that will look like new for years.

#### Limitations

- Do not apply when air, product or surface temperature is below 10 °C (50 °F) or above 32 °C (90 °F).
- Not for surfaces that will be immersed in liquids (sinks or tubs) or the surface of stoves or ovens.

#### Product Information

##### Colours — Standard:

White (01)

##### — Tint Bases:

Base 1B, 2B, 3B & 4B

Tint with Benjamin Moore® Gennex®, Color Preview® or Universal colorants

##### — Special Colours:

Contact your dealer.

##### Certifications & Qualifications :

The product supported by this data sheet contains a maximum of 50 grams per litre VOC/VOS excluding water & exempt solvents.

Master Painter Institute MPI # 140

##### Technical Assistance:

Available through your local authorized independent dealer.

For the location of the dealer nearest you, call 1-800-361-5898 or visit

[www.benjaminmoore.ca/INSLX](http://www.benjaminmoore.ca/INSLX)

##### Technical Data

##### White

Vehicle Type Urethane Reinforced Acrylic

Pigment Type Titanium Dioxide

Volume Solids 35.2 ± 1.0%

Coverage per Gallon at 32.5 – 41.8 sq. m.

Recommended Film Thickness (350 – 450 Sq. Ft.)

Recommended Film – Wet 3.6 – 4.6 mils

Thickness – Dry 1.3 – 1.6 mils

Depending on surface texture and porosity. Be sure to estimate the right amount of paint for the job. This will ensure colour uniformity and minimize the disposal of excess paint.

– Tack Free 1 Hour

Dry Time @ 25 °C – To Recoat 6 Hours

(77 °F) @ 50% RH – Full Cure 14 Days

High humidity and cool temperatures will result in longer dry, recoat and service times.

Dries By Coalescence

Viscosity 97 ± 3 KU

Flash Point 93.2 °C (200 °F) or greater

(TT-P-141, Method 4293)

Gloss / Sheen Satin (27 – 32 @ 60°)

Surface Temperature – Min. 10 °C (50 °F)

at Application – Max. 32.2 °C (90 °F)

Thin With Refer to Page 2

Clean Up Thinner Warm Soapy Water

Weight Per 3.79 L 10.9 lbs.

Storage Temperature – Min. 10 °C (50 °F)

– Max. 32.2 °C (90 °F)

##### Volatile Organic Compounds (VOC)

44.6 Grams/Litre

### Surface Preparation

**General** – All surface areas to be painted should be clean, dry, sound and free of all dirt, grease, oils, waxes, mildew and any other surface contaminants. Dirt and chalk should be thoroughly removed by scrubbing with warm soapy water. Surface wax should be removed with a commercial wax stripper. Grease or Oil residue should be removed using Grease & Oil emulsifier. Remove all loose chipping, cracking and peeling from previously painted surfaces by hand scraping, sanding, wire brushing and/or by use of power tool cleaning methods such as electric sanders, grinders, etc. Remove any loose rust, mill scale, rust deposits from metal surfaces. Repair/replace any seriously damaged and/or delaminated surface areas. Lightly feather sand all rough paint edges to adjacent surface area. All glossy surface areas should be lightly sanded to effectively dull any existing sheen and create a more suitable surface for painting.

**NOTE:** Always clean before sanding to prevent driving contamination into the substrate or previous coatings!

**Glossy Surfaces** – Although Cabinet Coat is formulated to be applied to hard to coat surfaces without the need for sanding, it is recommended that proper surface preparation still be completed to enhance adhesion properties. Surfaces such as Melamine Laminate, Formica®, ceramic tile and glossy painted surfaces should be properly deglossed.

**Previously Painted Surfaces:** No primer is needed if surface is in good condition. Clean or sand as described above. Spot prime bare spots with an initial coat of Cabinet Coat.

**Wood (non-bleeding), and engineered wood products:**

**Primer:** INSL-X® Aqua Lock® Plus or Cabinet Coat

**Finish:** 1-2 coats of Cabinet Coat

**Bleeding Type Woods (Redwood and Cedar):**

**Primer:** INSL-X® Prime Lock Plus or 1-2 coats of INSL-X® Aqua Lock® Plus

**Finish:** 1-2 coats of Cabinet Coat

**Melamine Laminate or Formica®:** No primer needed. Lightly sand with fine sandpaper. Remove sanding dust with tack rag.

**Ferrous Metal:** Prime bare spots with acrylic metal primer.

**WARNING!** If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by logging onto Health Canada @ <https://www.canada.ca/en/health-canada/services/environmental-workplace-health/environmental-contaminants/lead/lead-information-package-some-commonly-asked-questions-about-lead-human-health.html>

### Application

Cabinet Coat applies easily with a high-quality brush or roller. If spraying is desired, the preferred method is HVLP. Stir product thoroughly before using. It is important to maintain a wet edge during all methods of paint application by brushing or rolling into previously applied coating area. Overworking Cabinet Coat can lead to brush marks or roller marks, as this product dries quickly. Apply when surface and ambient temperature are above 10 °C (50 °F) and below 32.2 °C (90 °F). Avoid paint application if there is a threat of moisture condensing on the wet paint.

**Brush:** High-quality Synthetic Bristle only.

**Roller:** High-quality Short Nap Cover (Less than 12.7 mm / ½")

**Spray, HVLP:** Thin with up to 236.6 mL per 3.79 L of clean water. 1.8 Tip / 20 PSI

**Spray, Airless:** Fluid Pressure — 1,500 - 2,500 PSI;  
Tip — .011 - .015 Orifice

### Clean Up

Clean hands, brushes, rollers and other equipment with warm, soapy water immediately after use.

### Environmental Health & Safety Information

**Use only in a well ventilated area.** Keep container closed when not in use. In case of spillage, absorb with inert material and dispose of in accordance with local regulations. Wash thoroughly after handling.

**WARNING:** This product contains isothiazolinone compounds at levels of <0.1%. These substances are biocides commonly found in most paints and a variety of personal care products as a preservative. Certain individuals may be sensitive or allergic to these substances, even at low levels.

**KEEP OUT OF REACH OF CHILDREN  
PROTECT FROM FREEZING**

**Refer to Safety Data Sheet for  
additional health and safety information.**